


Desso Textile floor covering

Decor B 090 070

Specification according to EN 1307

Type of manufacture	ISO 2424	Woven - Axminster						
Aspect	ISO 2424	Cut pile						
Dye method		Hank dyed						
Width	cm	400	ft	13.1				
Primary backing	ISO 2424	Polypropylene weft / Polyester-based warp						
Secondary backing	ISO 2424	Copolymer						
Pile fibre composition	ISO 2424	80% wool - 20% polyamide						
Total thickness	ISO 1765	mm	9.0	inch	0.4			
Effective pile thickness	ISO 1766	mm	7.0	inch	0.28			
Total mass	ISO 8543	g/m ²	1900	oz/yd ²	56.1			
Total pile mass	ISO 2424	g/m ²	1490	oz/yd ²	44.0			
Effective pile mass	ISO 8543	g/m ²	1015	oz/yd ²	30.0			
Pile density	ISO 8543	g/cm ³	0.145	lb/in ³	0.0052			
Number of tufts	ISO 1763	/dm ²	975	/yd ²	81520			
Stroll test	ISO 6356	kV	-					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307	33 Commercial - heavy use						
Luxury rating	EN 1307	LC 5						
Impact sound reduction ΔL_w	ISO 10140	dB	32					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α_s	0.02	0.06	0.13	0.24	0.49	0.65
Noise reduction	ISO 354	α_w	0.20					
Thermal resistance	ISO 8302	m ² .K/W	0.159					
Flammability	EN 13501-1	Bfl - s1 (glued tested)						
Prodis - GUT	www.pro-dis.info	23316						



Desso flooring products are to be installed in full accordance with Desso's installation instructions and recognised trade standards. An effective, regular cleaning and maintenance programme is vital for retaining a high appearance level. Desso flooring products should only be used as floorcoverings. Note: Desso reserves the right to amend this specification without giving prior notice. For the latest versions of the technical specifications, visit www.desso.com

EN-20150929